

Date Generated: 17.05.24

B62 Product Data Sheet

Material Details

Grade:	B62. (Type: Composite / Specialist / Other Grades)
Description:	Phenolic Paper. Phenolic Paper core. Static dissipative 2 sides
Comments:	The Technolaque SD Range is a breakthrough in static dissipation. Developed by the Attwater Group, originally for the A.T.E. market, it incorporates a static-dissipative thermosetting surface, which is less than 50 microns thick. This special surface can be integrally press bonded onto a range of sheet substrates including Phenolic paper and epoxy glass during the manufacturing process, providing permanent static dissipative properties on one or both surfaces. As the Static-dissipative layer is not dependant upon additives bleeding to the surface, adhesive bonding of the manufactured components is possible. Also, the insulation properties of the core (below the static dissipative layer) are not affected permitting optimum insulation properties between conducting pins after suitable machining of the surface. B62 Phenolic paper / Epoxy glass composite core with Static dissipative surfaces on both sides.
Body Colour:	Black
Cover Colour:	Black
Standard Finish:	Satin/Glossy
Size:	1220 x 1220 Thickness Range: 1.6 - 50.0 †

Typical Applications

- Static Sensitive Applications
- Jigs and Fixtures
- Conveyor Trays

General Properties

Property	Unit of measure	Typical Value
Density	g/cm ³	1.35

‡ Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

Electrical Properties

Property	Unit of measure	Typical Value
IR (24hrs Water Immersed)	G □	0.1 (Core)

Property	Unit of measure	Typical Value
IR (Dry)	G □	0.1 (Core)
Surface Resistivity	□ 2	10 ⁵ - 10 ¹⁰

Mechanical Properties

Property	Unit of measure	Typical Value
Flexural Strength at 150°C	MPa	190
Tensile Strength	MPa	120

Thermal Properties

Property	Unit of measure	Typical Value
Thermal Rating Continuous	°C	100
Thermal Rating Intermittent	°C	120

Notes

- Datasheet Issue No. 2

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/b62/>